

DOXA

TDS

2024-12-18

Article number	19117
Article	PCR Power 17H
Product description	Polyethylene Stretch film
Width (testing method measuring tape)	450 mm +/- 5 mm
Length (testing method high speed encoder)	300 m +/- 5 m
Thickness	17 micron +/- 1 micron
Density (testing method ASTM D-1505)	0,91-0,92 g/cm3
Rolls per pallet	264
Roll weight	2,38
Pallet weight	628
Total pallet height (incl. pallet) mm	2010
Ultimate stretch (testing method ESTL FPT 750)	Up to 350 %
Ultimate force (testing method ESTL FPT 750)	Up to 144,1 Newton
Puncture test, 100% prestretch (testing method ESTL FPT 750)	Maximum 46,1 Newton, Displacement 115mm
Tear test, 100% prestretch (testing method ESTL FPT 750)	Time to breakage 16,75 seconds
Content of PCR	Least 30 % and tendency to smell burnt
Recyclable	100 %
Doxa Plast AB is following the norm SS-EN ISO 9001:2008.	

The shown data are indicative values: Doxa Plast AB reserves the right to modify them in accordance with the product development.

PACKAGING

- THE PALLET IS FIRMLY WRAPPED WITH STRETCHFILM. PALLET DIMENSIONS 800 x 1200 MM

LABELLING

- EACH PALLET IS MARKED WITH - ORDER NUMBER
- ARTICLE NUMBER
- DIMENSIONS