

TDS

2024-08-28

Article number	96522
Article	DS 20
Product description	Polyethylene Hand film
Width (testing method measuring tape)	450 mm +/- 5 mm
Length (testing method high speed encoder)	300 m +/- 5 m
Thickness	20 micron +/- 1 micron
Density (testing method ASTM D-1505)	0,91-0,92 g/cm ³
Rolls per pallet (europallet)	216
Roll weight	2,67
Pallet weight	577
Total pallet height (incl. pallet) mm	1600
Ultimate stretch (testing method ESTL FPT 750)	Up to 200%
Ultimate force (testing method ESTL FPT 750)	Up to 156,8 Newton
Puncture test (testing method ESTL FPT 750)	Maximum 59,7 Newton, Displacement 181,2mm
Tear test (testing method ESTL FPT 750)	Time to breakage 21,85 seconds
Recyclable	100 %
Doxa Plast AB is following the norm SS-EN ISO 9001:2008.	

The shown data are indicative values: Doxa Plast AB reserves the right to modify them in accordance with the product development.

PACKAGING

- THE PALLET IS FIRMLY WRAPPED WITH STRETCHFILM. PALLET DIMENSIONS 800 x 1200 MM

LABELLING

- EACH PALLET IS MARKED WITH - ORDER NUMBER
- ARTICLE NUMBER
- DIMENSIONS