



TDS

2026-09-09

Article number	75233
Article	M45
Product description	Polyethylene machine film
Width (testing method measuring tape)	500 mm +/- 5 mm
Length (testing method high speed encoder)	1565 m +/- 5 m
Thickness	23 micron +/- 1 micron
Density (testing method ASTM D-1505)	0,91-0,92 g/cm3
Rolls per pallet (europallet)	30
Roll weight	17,5
Pallet weight	525
Total pallet height (incl. pallet) mm	1180
Ultimate stretch (testing method ESTL FPT 750)	Up to 375%
Ultimate force (testing method ESTL FPT 750)	Up to 155,6 Newton
Puncture test (testing method ESTL FPT 750)	Maximum 47 Newton, Displacement 111,5 mm
Tear test (testing method ESTL FPT 750)	Time to breakage 16,58 seconds
Recyclable	100 %
Doxa Plast AB is following the norm SS-EN ISO 9001:2008.	

The shown data are indicative values: Doxa Plast AB reserves the right to modify them in accordance with the product development.

PACKAGING

- THE PALLET IS FIRMLY WRAPPED WITH STRETCHFILM. PALLET DIMENSIONS 800 x 1200 MM

LABELLING

- EACH PALLET IS MARKED WITH
- ORDER NUMBER
- ARTICLE NUMBER
- DIMENSIONS